



TECHNICAL DATA SHEET

Rakoll Express™ DKN

Page 1 of 3 Last updated 13/11/2018

Type of Product PVAc glue.

Product Characteristics - very low viscosity

- suitable for low pressure automatic doweling machines

Typical Applications Mechanical dowel gluing in low pressure automatic doweling machines.

Suitable substrates Wood and wood-based materials.

Typical Properties

Property	Value
Base	Polyvinylacetate dispersion (PVAc)
Colour	white, dry, transparent
Н	approx. 7
White point	approx. +10°C
Viscosity (Brookfield RV, Sp2, 50rpm, at 20°C)	150 +/- 25 mPa.s
Shelf life	12 months







TECHNICAL DATA SHEET

Page 2 of 3 Rakoll Express™ DKN

Rakoll Express™ DKN

Application Instructions

Rakoll Express™ DKN is supplied ready for use. The glue should be stirred thoroughly before use, e.g. filling the pressure container of an automatic doweling machine.

Recommended working conditions:

- Room-material and glue temperature: 18°C 20°C
- Wood moisture content: 8 12%Relative air humidity: 40 70%

Machine settings:

The machine must be set up in accordance with the instructions of the manufacturer. Generally, a pressure of about 3,0 bar in the pressure containers is enough. It is helpful to clean the spray nozzles with a moist rag at the beginning of each break to avoid deflection of the spray caused by adherence of dried glue. As the viscosity of Rakoll Express™ DKN is temperature-dependent, the spray quantity should be checked at frequent intervals. If the quantity of injected glue is too small, it will result in reduced strength of the joints.

Dowels:

Wooden dowels should be made from sound, strong wood and be thoroughly dried. They must be produced to exact size and have a very fine fluting and fitting exactly into the intended holes.

The strength of the joint depends to a large extent on the fit accuracy of the dowel and the glue usage. If using plastic dowels, the adhesion depends on the composition and the surface texture of the dowel. As the conditions in the joint during setting are different from those for wooden dowels, which expand slightly and therefore achieve a higher initial strength, it is in any case recommended that adequate preliminary trials be carried out when using plastic dowels.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

* and ** are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties (of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.







TECHNICAL DATA SHEET

Rakoll Express™ DKN

Page 3 of 3

Application Instructions Wood preparation:

The parts should be cleanly drilled, mate well and be free from dust and grease. Excessive fit tolerances will lead to longer setting times and weaker bonds.

Wood discolouration:

Rakoll Express $^{\text{\tiny{M}}}$ DKN does not cause discolouration of the wood. Iron in combination with the tannic acid of the veneer can however lead to

changes of colour, particularly in the case of oak.

Cleaning Instructions Clean the spray nozzles with water before the glue dries.

Typical Packaging Please contact your local Sales Office for available packaging options.

Storage Conditions Store in tightly closed original containers between +5°C and +35°C.

Not reusable after warming.

Disposal Advice Please refer to the MSDS for disposal instructions.

Safety Advice Please refer to the MSDS for safety advice.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

* and ** are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.



NOTE TO USER: by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.

